

Size : 15000 x 2000 x 1.5 mm

Physical & Technical Properties

Properties	Test Method	Result
Abrasion Resistance	EN 649	Group T
Resistance To Chemicals	EN 423	Good Resistance
Flexibility	EN 435	40 mm Mandrel, Passed
Slip Resistance	DIN 51130	R9
Abrasion Resistance	EN 660-2 EN 649	Wear Group M
Caster Chair	EN 425	No surface damage/ Continuous Use
Colour Fastness To Day Light	ISO 105-BO2	Blue Wool Standard 5
Surface Spread Of Flame	BS 476 PART 7	Class 1
Stain And Chemical Resistance	EN 423	No Visible Change
Fungi And Bacterial Resistance	EN ASTM G-21	Does Not Favor Growth
Sound Absorption	ISO 140-8 EN ISO 717-2	Δ LW = 5db
Performance Classification	EN 685	32,33



Properties	Test Method	Unit	Value
Residual Indentation	EN433	mm	0.10
Dimensional Stability	EN434	≤	0.40
Sound Absorption	ISO 140 - EN ISO 717-2	db	5
Thermal Conductivity	EN 12524	W /m-k	0.25
Weight	EN 430	gsm	2.70
Dimensional Stability	EN 434	%	0.40
Residual Indentation After Static Load	EN 443	mm	0.10

Damage Resistant	<input checked="" type="checkbox"/>
Slip Resistant	<input checked="" type="checkbox"/>
Scratch Resistant	<input checked="" type="checkbox"/>
Durable	<input checked="" type="checkbox"/>
Low maintenance	<input checked="" type="checkbox"/>
Easy installation	<input checked="" type="checkbox"/>
Hygienic	<input checked="" type="checkbox"/>
Anti microbial	<input checked="" type="checkbox"/>
Water Penetration	<input type="checkbox"/>

Application

- Healthcare
- Public Transport
- Commercial
- Industrial
- Residential
- Retail

+971 54 569 1963

danubebuildingmaterial

danubebuildingmaterial

danubebuildingmaterial

danubebuildingmaterials

Danube Building Materials FZCO

P.O. Box 18022, Jebel Ali Free Zone, Dubai, U.A.E. | Tel : +971 4 8871234, Fax : +971 4 8810158 | Email: enquiry@aldanube.com

www.danubebuildingmaterials.com