

Size : 2400 x 600 mm

Type : Liner Travertine
Color : Clay Bank, Light Grey, Roman Yellow
Origin : China



Clay Bank Light Grey Roman Yellow

Physical & Technical Properties

Properties		Test Method	Unit	Test Result
Water Absorption		GBIT 966.3-2001	%	8%
Stain Resistance		GBIT 9780-2005	Grade	GRADE 1
Abrasion Resistance g/750r		GB/T 3810.7-2006	g	0.05
Radioactivity		GB 6566	IRa	0.2
			r	0.2
Flame Retardance		GB 8624-2012	Grade	A
Soluble Heavy Metal	TVOC	GB6566	g/m2	1.8
	Pb			0
	Cd			0

- Flexible and bendable
- Strong Touchness
- Water proof
- Light Weight
- Aging Resistance
- Environmental Friendly

Chemical	3%(v/v)HCL	GBIT 3810.13	No bubbling or peeling even after soaking for 12 as per test
Resistance	3%(v/v)KOH		
Flexibility	20°C ,3S,180.	JCIT 864	No crack or break.
Age Resistance		GB/T 16259-2080	No crack or chalking after 3500 hours age test

- Environment friendly
- Light weight
- Energy saving
- Easy Installation

Application

Residential

- ◆ Accent walls
- ◆ Headboard panels
- ◆ Fireplace surrounds.

Commercial

- ◆ Retail stores
- ◆ Restaurants
- ◆ Offices

Hospitality

- ◆ Hotels
- ◆ Resorts
- ◆ Spas